

IN THE SPECIFICATION

Page 42, please amend the paragraph beginning at line 24 to page 43, line 5 to read as follows:

b1
Also, a bag measuring 8 x 8 cm was fabricated, using a sheet exhibiting a moisture permeability of $8200 \text{ g/m}^2 \cdot 24\text{h}$ (~~JIS (Japanese Industrial Standard) Z0208 method~~ (40°C, 90% relative humidity)) and an air permeability of 25 seconds/100 cm^3 (~~JIS P8117 method~~). In this bag was contained 25 g of the exothermic composition noted above to fabricate the steam generating unit 102A, which was sealed in an airtight bag.